
**Plastics — Determination of burning
behaviour of thin flexible vertical
specimens in contact with a small-flame
ignition source**

AMENDMENT 1: Specimens

*Plastiques — Détermination du comportement au feu d'éprouvettes
minces verticales souples au contact d'une petite flamme comme
source d'allumage*

AMENDEMENT 1: Éprouvettes

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 9773:1998 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 4, *Burning behaviour*.

Plastics — Determination of burning behaviour of thin flexible vertical specimens in contact with a small-flame ignition source

AMENDMENT 1: Specimens

Page 1

In the second sentence of Clause 1, replace “using method B of ISO 1210” by “using method B of IEC 60695-11-10:1999”.

Update Clause 2 (normative references) as follows:

Replace ISO 1210:— by IEC 60695-11-10:1999 and delete the footnote.

Replace ISO 1043-1:1997 by ISO 1043-1:2001 (same title).

Insert 1998 as the year of publication of ISO 10093 and delete the footnote.

Replace ASTM D 5207-91 by ASTM D 5207-98 (same title).

Page 4

Replace Clause 7 “Specimens” by the following clause.

7 Specimens

7.1 It is possible that the results of tests carried out on test specimens taken from materials of different densities, colours, thicknesses, melt flow abilities and directions of anisotropy, or with different additive or filler/reinforcement contents, will be different. For materials with properties or compositions which vary over a range, the test specimens shall be representative of the whole range.

7.2 Test specimens with densities, melt flow abilities and additive or filler/reinforcement contents at the extremes of the range shall be tested and, if the test results yield the same flame test classification, all specimens within the range shall be considered representative of the range. If the burning characteristics are not essentially the same, the results of the evaluation shall be considered to apply only to the materials with the densities, melt flow abilities and additive or filler/reinforcement contents tested. Additional test specimens with intermediate densities, melt flow abilities and additive or filler/reinforcement contents shall be tested to determine the range of applicability.

7.3 Uncoloured test specimens and test specimens with the highest level of organic and inorganic pigment loading shall be tested and, if the test results yield the same flame test classification, all specimens with this colour range shall be considered representative of the range. If a material contains pigments which are known to affect the flammability characteristics, specimens containing these pigments shall also be tested. Thus the test specimens tested shall be those that

- a) contain no colouring;
- b) contain the highest level of organic pigments;
- c) contain the highest level of inorganic pigments;

d) contain pigments which are known to adversely affect flammability characteristics.

7.4 All specimens shall be cut from a representative sample of the material (sheets or end products). After any cutting operation, care shall be taken to remove all dust and any particles from the surface. Cut edges shall have a smooth finish.

7.5 The standard test specimen shall be $200\text{ mm} \pm 5\text{ mm}$ long, $50\text{ mm} \pm 2\text{ mm}$ wide and a maximum of 0,25 mm thick. Measure the thickness of each to the nearest 0,01 mm and note the measurements.

NOTE 3 Tests made on test specimens of different thicknesses or directions of anisotropy may not be comparable.

7.6 Mark each specimen across its width with a line at $125\text{ mm} \pm 5\text{ mm}$ from one end (the bottom end). Wrap the longitudinal axis of the specimen tightly around the longitudinal axis of the mandrel to form a lapped cylinder with the 125 mm line exposed. Secure the overlapping portions of the specimen within the upper 75 mm segment above the 125 mm mark and at the upper end of the tube with pressure-sensitive adhesive tape. Then remove the mandrel.

NOTE 4 For stiff specimens, the pressure-sensitive tape may be reinforced or replaced by nichrome wire wound around the top 75 mm of the specimen (see Figure 1).

7.7 Prepare a minimum of 20 specimens. It is advisable to prepare additional specimens for any retesting which may be necessary.

Page 8, Table A.1

In footnote 2), replace “method A of ISO 1210” by “method A of IEC 60695-11-10:1999”.

